

Dr. Dietrich Müller GmbH, Zeppelinring 18, D-26197 Ahlhorn

Gasket materials

Temacarb Black FS 30300

Property	Test method	Unit	Value
Max. working pressure	-	MPa	10
Max. working temperature Continual	-	°C	250
Peak	-		450
Density	DIN 28 090-2	g/cm ⁻³	1.6 – 1.9
Residual stress 16h at 175°C	Din 52 913	MPa	32
Compressibility	ASTM F 36 – J	%	5 – 15
Recovery	ASTM F 36 – J	%	50
Spec. Leakage rate	DIN 3535 – 6	mg/s.m	0.05
ASTM OIL – IRM 903, ČSN ISO 1817 5h at 150°C	ASTM F 146	%	3
ASTM FUEL B - ČSN ISO 1817 5h at 23°C	ASTM F 146	%	5
Flexibility	ASTM F 147	-	No cracks or breaks

Please note:

The information in this data sheet is based on our current knowledge and experience. They do not disengage the fabricator and user from own tests and inspections because of the plenty of possible effects. There is no judicial binding assurance of certain properties or of the qualification for a concrete application in our declaration. We recommend consulting us in individual cases. The acceptor of our products has to observe possible industrial property rights as well as present laws by himself.

Status September 2014

Zeppelinring 18 | D-26197 Ahlhorn | Tel.: +49 (0) 4435 97 10 10 | Fax: +49 (0) 4435 97 10 11
 info@mueller-ahlhorn.com | www.mueller-ahlhorn.com | Sitz der Gesellschaft: Ahlhorn
 Geschäftsführer: Heinz-Jürgen Siebert | AG Oldenburg: HRB 209026 | Ust. ID-Nr.: DE 295969093
 St.-Nr.: 68/207/07677 | Zertifiziert nach DIN EN ISO 9001:2008 | UL anerkannter Repacker E341377

Dr. Dietrich Müller GmbH

- Elektroisierstoffe
- Dichtungen
- Wärmeleitprodukte
- Technische Folien