

Dr. Dietrich Müller GmbH, Zeppelinring 18, D-26197 Ahlhorn

## Electrical Insulating Material

### Rigidiso<sup>®</sup> RI 40205

---

**Structure:** Rigidiso<sup>®</sup> RI 40205 is a laminate made of Epoxy-Resin Glass-Fibre laminate and conforms to the following standards:

IEC 60893	EP GC 203
DIN 7735	HGW 2372.4

---

**Characteristics:** Rigidiso<sup>®</sup> RI 40204 is classified to Insulation Class B (180°C). It also has very good mechanical properties.

---

**Application:** Rigidiso<sup>®</sup> RI 40204 is used as a construction material with high requirements to the insulation properties.

---

**Form of Supply:** Rigidiso<sup>®</sup> RI 40204 is supplied in thicknesses of 0.20 – 80.00 mm and in a sheet format of 2140 x 1240 mm.

---

**Storage Conditions:** Rigidiso<sup>®</sup> RI 40204 can be stored unlimited under normal conditions (20°C, 50% r. H.).

---

Stand February 2015

Zeppelinring 18 | D-26197 Ahlhorn | Tel.: +49 (0) 4435 97 10 10 | Fax: +49 (0) 4435 97 10 11  
info@mueller-ahlhorn.com | www.mueller-ahlhorn.com | Sitz der Gesellschaft: Ahlhorn  
Geschäftsführer: Heinz-Jürgen Siebert | AG Oldenburg: HRB 209026 | Ust. ID-Nr.: DE 295969093  
St.-Nr.: 68/207/07677 | Zertifiziert nach DIN EN ISO 9001:2008 | UL anerkannter Repacker E341377

Dr. Dietrich Müller GmbH

- Elektroisolierstoffe
- Dichtungen
- Wärmeleitprodukte
- Technische Folien

Dr. Dietrich Müller GmbH, Zeppelinring 18, D-26197 Ahlhorn

## Rigidiso<sup>®</sup> RI 40205

Technical Data:	Norm	Unit	Value
Density	ISO 1183 / A	g/cm <sup>3</sup>	1.7 – 1.9
Flexural Strength	ISO 178	Mpa	350
Elasticity of the Flexural Test	ISO 178	Mpa	18 x 10 <sup>3</sup>
Tensile Strength	ISO 527	Mpa	220
Impact Strength	ISO 179 / 3C	kJ/m <sup>2</sup>	100
Temperature Limit	IEC 216	°C	250
Comparative Tracking Index	DIN / IEC 112	-	200
Thermal Conductivity	-	W/mK	0.3
Insulation class	-	-	C
Water Absorption (5mm)	ISO 62 / 1	mg	30

**Trademark Information:** Rigidiso<sup>®</sup> is a registered trademark of the company Dr. Dietrich Müller GmbH, Germany

**Please note:** The information in this data sheet is based on our current knowledge and experience. They do not disengage the fabricator and user from own tests and inspections because of the plenty of possible effects. There is no judicial binding assurance of certain properties or of the qualification for a concrete application in our declaration. We recommend consulting us in individual cases. The acceptor of our products has to observe possible industrial property rights as well as present laws by himself.

Stand February 2015

Zeppelinring 18 | D-26197 Ahlhorn | Tel.: +49 (0) 4435 97 10 10 | Fax: +49 (0) 4435 97 10 11  
 info@mueller-ahlhorn.com | www.mueller-ahlhorn.com | Sitz der Gesellschaft: Ahlhorn  
 Geschäftsführer: Heinz-Jürgen Siebert | AG Oldenburg: HRB 209026 | Ust. ID-Nr.: DE 295969093  
 St.-Nr.: 68/207/07677 | Zertifiziert nach DIN EN ISO 9001:2008 | UL anerkannter Repacker E341377

Dr. Dietrich Müller GmbH

- Elektroisierstoffe
- Dichtungen
- Wärmeleitprodukte
- Technische Folien