

Electrical Insulation Materials

Flexiso® GK FI 16020

Structure: Flexiso® GK FI 16020 is made of a polyimide film which is laminated on one side with glass cloth. The used laminating adhesive is high-temperature resistant.

Characteristics: Flexiso® GK FI 16020 has good mechanical and electrical properties as well as good flexibility in a wide temperature range. The used glass cloth can be compromised and has a good impregnation for impregnating resins.

Application: Flexiso® GK FI 16020 is used as slot and phase insulation or as layer insulation in low-voltage machines and transformers which have to meet high thermal requirements.

Standard colour: Flexiso® GK FI 16020 is delivered in white/brown colour.

Delivery Forms: Flexiso® GK FI 16020 is supplied in rolls (width max. 980 mm) and as reels (from 10 mm wide). Other formats, for example, blanks, die-cut and formed parts are supplied to customer specifications.

Storage conditions: Flexiso® GK FI 16020 can be stored unlimited under normal conditions (20° C, 50 % rel. air humidity).

Dr. Dietrich Müller GmbH

Flexiso® GK FI 16020

Properties	Test method	Unit	Value
Total thickness	IEC-626-2	mm	0.13
		%	± 15%
Film thickness	IEC-626-2	µm	25
Basis weight	IEC-626-2	g/m ²	150
			± 12%
Yield	-	m ² /kg	6.7
Tensile strength MD	IEC-626-2	N/mm ²	≥120
Tensile strength CD	IEC-626-2	N/mm ²	≥100
Elongation MD	IEC-626-2	N/10mm	≥2
Elongation CD	IEC-626-2	N/10mm	≥2
Humidity content	IEC-626-2	%	0.1
Breakdown voltage	IEC-626-2	kV	≥7

Trademark information: Flexiso® is a registered trademark of Dr. Dietrich Müller GmbH, Germany.

Information:

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Dr. Dietrich Müller GmbH makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Dr. Dietrich Müller GmbH only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Dr. Dietrich Müller GmbH be liable for any incidental, indirect or consequential damages arising from the sale, resale, use, or misuse of the product. Dr. Dietrich Müller GmbH Specifications are subject to change without notice. In addition, Dr. Dietrich Müller GmbH reserves the right to make changes in materials or processing without notification to the Buyer, which do not affect compliance with any applicable specification.

Dr. Dietrich Müller GmbH



Dr. Dietrich Müller GmbH
Zeppelinring 18
D-26197 Ahlhorn

Tel.: +49 (0) 44 35 - 97 10 10
Fax: +49 (0) 44 35 - 97 10 11
Info@mueller-ahlhorn.com

Dr. Dietrich Müller GmbH

Zeppelinring 18 | D-26197 Ahlhorn | Tel.: +49 (0) 4435 97 10 10 | Fax: +49 (0) 4435 97 10 11
info@mueller-ahlhorn.com | www.mueller-ahlhorn.com | Sitz der Gesellschaft: Ahlhorn
Geschäftsführer: Dr. Michael Müller | AG Oldenburg: HRB 209026 | Ust. ID-Nr.: DE 295969093
St.-Nr.: 68/207/07677 | Zertifiziert nach DIN EN ISO 9001:2015 | UL anerkannter Repacker E341377

- Elektroisolierstoffe
- Dichtungen
- Wärmeleitprodukte
- Technische Folien