

## Gasket material

### BISCO® HT-800 medium cellular silicone

---

**Material:** BISCO® HT-800 medium cellular silicone is a foam-material.

---

**Properties:** BISCO® HT-800 medium cellular silicone offers excellent memory and low stress relaxation, high compressibility, resistance to UV-light, ozone, extreme temperatures and flame.

---

**Applications:** BISCO® HT-800 medium cellular silicone foam is used as environmental seal to protect against penetration of dust, moisture, air or light for lighting fixtures, HVAC units and electronic cabinets. It can also be applied for electronic components and transportation vehicles as vibration isolation or shock absorbing cushions and gaskets.

---

**Delivery forms:** BISCO® HT-800 medium cellular silicone foam can be delivered as customized cut or die-cut part as well as self-adhesive. Other delivery forms upon customer request.

---

## BISCO® HT-800 medium cellular silicone

properties	Test method	unit	Value
<b>Physical properties</b>			
Colour			Black, grey, red
Thickness		Mm	0,80 – 12,7
Standard width		Mm	914
Density	ASTM D 1056	Kg/m <sup>3</sup>	352
Compression force deflection, 25%	ASTM D 1056	kPa	62
Compression set, 70°C/100°C	ASTM D 1056	% max.	<1/<5
Tensile strength	ASTM D 412	kPa	310
Elongation	ASTM D 412	%	80
<b>Flammability and outgassing</b>			
Flame resistance	UL 94		V-0, HF-1
Flame spread index	ASTM E 162	L <sub>s</sub>	<25
Smoke density, 4 min./1,5 min.	ASTM E 662	D <sub>s</sub>	<50/<20

properties	Test method	unit	Value
<b>Environmental properties</b>			
Water absorption, RT 24 h		%	1,40
<b>Electrical &amp; thermal properties</b>			
Dielectric constant	ASTM D 150		1,42
Dielectric strength	ASTM D149	V/mil	3583
Dry arc resistance	ASTM D 495	Sec.	92
Volume resistivity	ASTM D 257	Ohm-cm	10 <sup>14</sup>
Thermal conductivity	ASTM C 518	w/mK	0,09
<b>Temperature resistance</b>			
Low temperature flex at -55°C	ASTM D 1056		Pass
Recommended use temperature		°C	-55 to +200

Dr. Dietrich Müller GmbH

## BISCO® HT-800 medium cellular silicone

---

**Please note:**

The information in this data sheet is based on our current knowledge and experience. They do not disengage the fabricator and user from own tests and inspections because of the plenty of possible effects. There is no judicial binding assurance of certain properties or of the qualification for a concrete application in our declaration. We recommend consulting us in individual cases. The acceptor of our products has to observe possible industrial property rights as well as present laws by himself.

---

Dr. Dietrich Müller GmbH