

Laminates

Rigidiso® RI 40208

Composition: Rigidiso® RI 40208 is a laminate made of silicone-resin glass cloth and conforms to the following standards:

IEC 60893	SI GC 202
DIN 7735	HGW 2572
BS (GB)	3953-SI 5
NEMA L1 (USA)	G 7
NF C26 (F)	154-VS 1/2
VSM (CH)	S-SI GC 2
MIL SPEC	24768/17

Properties: Rigidiso® RI 40208 is insulating up to insulation class H (180°C), furthermore it has very good mechanical properties. In addition to that it is environmentally neutral, free of asbestos, dioxin, cadmium and halogen. Rigidiso® RI 40208 is designed in accordance with flammability class UL 94 level V-0.

Applications: Rigidiso® RI 40208 is used as construction material with higher requirements to the insulation properties.

Delivery forms: Rigidiso® RI 40208 is available in thicknesses of 0.2 mm – 60 mm as well as sheet (2440 x 1220 mm and 1150 x 2200 mm with a max. sheet size of 2440 x 1240 mm). Furthermore Rigidiso® RI 40208 can also be delivered as cut, milled, die-cut or water-jet cut parts. In addition it can be equipped with a special varnish to meet an CTI of more than 600.

Dr. Dietrich Müller GmbH

Rigidiso® RI 40208

Standard colour: Rigidiso® RI 40208 is delivered in white colour.

Storage requirements: Rigidiso® RI 40208 is durable unlimited under normal conditions (20°C, 50% rel. air humidity).

Property	Test method	Unit	Value
Density	ISO 1183 / A	g/cm ³	Ca. 1.7
Elasticity module of flexural test	ISO 178	Mpa	13 x 10 ³
Tensile strength	ISO 527	Mpa	90
Limiting temperature	IEC 216	°C	180
Comparative tracking index	DIN / IEC 112	CTI	440
Thermal conductivity	DIN 52612	W/mK	0.3
Thermal class	IEC Publ.85	level	H
Water absorption (5mm)	ISO 62 / 1	mg	50
Resistance between plugs after 24 hours water storage at 23°C	DIN 53482	Ohm	10 ⁸
1 Minute test voltage in layer direction at 90°C after pre-treatment	DIN 53481	kV	25
1 Minute test voltage vertical to layer at 90°C after pre-treatment	DIN 53481	kV	20
Dielectric dissipation factor tan d 50 Hz 96 hours 105°C 1 MHz 24 hours water storage	DIN 53483	max.	0.05
			0.07
Dielectric constant	DIN 53483	»	5
Flexural strength untreated at 23°C	DIN 53452	MPa	125
Impact resistance a _{n10} and a _{n15}	DIN 53453	kJ/m ²	40
Notch impact resistance a _{k 10}	DIN 53453	kJ/m ²	25

Dr. Dietrich Müller GmbH

Rigidiso® RI 40208

Property	Test method	Unit	Value
Pressure resistance	DIN 53454	MPa	50
Splitting strength	DIN 53463	N	1000
Coefficient of linear expansion	VDE 0304/2	10 ⁻¹⁰ /K	10 – 20
Electrolytic corrosion	DIN 53489	max.	AN 1,4
Limiting value of limiting temperature according to flexural strength	-	MPa	65
Incandescence resistance	DIN 53459	level	2a

Thickness	0.3	0.5	0.8	1.0	1.5	2.0	2.5	3.0	3.5	4.0
Availability	○	●	●	●	●	●	●	●	●	●

Thickness	4.5	5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0
Availability	●	●	●	●	●	●	●	●	●	●

Thickness	14.0	15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	25.0
Availability	●	●	●	●	●	●	●	●	●	●

Thickness	30.0	35.0	40.0	45.0	50.0	60.0	70.0	80.0	90.0	100.0
Availability	●	●	●	○	○	○	○	○	○	○

- Pre-material on stock
- Delivery time pre-material 2 weeks

Trademark Information: Rigidiso® is a registered trademark of the company Dr. Dietrich Müller GmbH, Germany.

Dr. Dietrich Müller GmbH

Rigidiso® RI 40208

Please note:

The information in this data sheet is based on our current knowledge and experience. They do not disengage the fabricator and user from own tests and inspections because of the plenty of possible effects. There is no judicial binding assurance of certain properties or of the qualification for a concrete application in our declaration. We recommend consulting us in individual cases. The acceptor of our products has to observe possible industrial property rights as well as present laws by himself

Dr. Dietrich Müller GmbH