

Dr. Dietrich Müller GmbH Zeppelinring 18 D-26197 Ahlhorn Tel.: +49 (0) 44 35 - 97 10 10 Fax: +49 (0) 44 35 - 97 10 11 Info@mueller-ahlhorn.com



CONTACT

Deutschland

Dr. Dietrich Müller GmbH Hauptsitz und Werk Flexibles Zeppelinring 18 26197 Ahlhorn +49 4435 97 10-318 +49 4435 97 10-11 info@mueller-ahlhorn.com

USA

Dr. Dietrich Mueller GmbH - Sales office USA 1201 N. Orange Street Suite 7160 19801 Wilmington, Delaware United States +1 302 4988371 +1 302 4988372 info.usa@mueller-ahlhorn.com

United Kingdom

Dr. Dietrich Mueller (UK) Ltd. 49 Greek Street London W1D 4EG United Kingdom +44 20 80894197 +44 20 80894198 info.uk@mueller-ahlhorn.com

China

Dr. Dietrich Mueller GmbH. Level 8, International Finance Center, Tower 2, 8 Century Avenue 200120 Shanghai, Pudong China info.china@mueller-ahlhorn.com

ABOUT OUR COMPANY

Dr. Dietrich Müller GmbH is a global solution provider for electrical insulation materials, thermally conductive products, seals and technical films.

We advise on the selection of the right material and manufacture precision parts from flexible and rigid materials. We operate 6 sites and provide services to companies around the world.

We are ISO 9001 and ISO 14001 certified and UL listed as a repackager (E341377).

Dr. Dietrich Müller GmbH

Zeppelinring 18 | D-26197 Ahlhorn | Tel.: +49 (0) 4435 97 10 10 | Fax: +49 (0) 4435 97 10 11 info@mueller-ahlhorn.com | www.mueller-ahlhorn.com | Sitz der Gesellschaft: Ahlhorn Geschäftsführer: Dr. Michael Müller | AG Oldenburg: HRB 209026 | Ust. ID-Nr.: DE 295969093 St.-Nr.: 68/207/07677 | Zertifiziert nach DIN EN ISO 9001:2015 | UL anerkannter Repacker E341377 Elektroisolierstoffe

Dichtungen

- Wärmeleitprodukte
- Technische Folien





PORON[®] ShockPad 0.3mm Plus Adhesive

New mobile internet devices are as slim as ever, and designers are being asked to fit even more features and gadgets into these tiny packages. As part of space-saving designs, the display, the printed wiring board, and other electrical components are compacted into very thin spaces. Unfortunately, these components often lack proper impact protection technology. How can Rogers help?



As you can see in the graph above, **PORON ShockPad Foam absorbs twice as much force as equivalent competitive material** in real-life drop conditions.

This could mean the difference between a device surviving a fall or a device's LCD screen and internal components failing on impact. Visit www.rogerscorp.com/ShockPad to learn more!

The impact data and images above were compiled using the following test:

Smartphone Impact Simulation Impacting Object: 30.8 g brass ball Height of Drop: 0.3 meters Display Module: 0.5 mm glass on both sides of foam.



The information contained in this Data Sheet is intended to assist you in designing with Rogers'Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries.

© 2013 Rogers Corporation, All rights reserved. Printed in U.S.A., 1213-PDF, Publication #17-243

Data Sheet: PORON[®] ShockPad 0.3mm Plus Adhesive Typical Values

	Property	Method	Detail	Unit	Value	
Urethane	Compression Force Deflection	Strain rate = 0.2"/minute	@ 25% Deflection	typical, psi (kPa)	4.34 (29.9)	
	Compression Set	ASTM D 3574-95	Tested @ 70°C (158°F)	Typical% Maximum %	2 10	
	Color (Code)				Black (04)	
Supported Adhesive	Peel Adhesion	ASTM D 1000 180° Peel	To Stainless Steel To Polypropylene To PolyCarbonate To ABS To Acrylic	N/25mm (oz/in)	20 min @ RT/ 72 hrs @ RT 8.0 (28.9) / 9.1 (32.7) 7.8 (28.0) / 8.0 (28.7) 8.5 (30.7) / 10.1 (36.2) 8.2 (29.4) / 9.7 (34.8) 8.2 (29.4) / 9.7 (34.8)	
	Release Adhesion	ASTM D 1000 180° Peel	Room Temp 96 hr @ 66°C/80% RH	gram/in	9.4 10.6	
	Tack	ASTM D 2979 (1 sec dwell)	Room Temp 96 hr @ 66°C/80% RH	grams	424 411	
	Tensile	ASTM D 882	Room Temp MD/CMD 96 hr @ 66°C/80% RH	kg (lb)	5.4 (12.0) / 4.1 (9.1) 5.1 (11.4) / 5.0 (11.0)	
	Elongation	ASTM D 882	Room Temp MD/CMD 96 hr @ 66°C/80% RH	%	78 / 32 74 / 66	
	Shelf Life		from date of manufacture	months	12	

Matavial	Description	Thickness		Tolerance	
Material	Description	mm	mil	mm	mil
Urethane Foam	PORON ShockPad	0.27	10.5	± 0.076	± 3.0
Supported Adhesive	PET and Adhesive	0.038	1.5	+ 0.005/- 0.01	+ 0.2/- 0.4
Total Construction*	Foam, PET, Adhesive	0.30	12	± 0.076	± 3.0

* The Liner is typically removed by the end user & not included as part of the total thickness

Storage Information

PORON ShockPad 0.3mm Plus Adhesive material has a shelf life of 12 months from the date of manufacture when stored at room temperature. Storage in the original packaging located in a dry cool environment is recommended.

Note: All unit conversions are approximate. Additional technical information is available.

0.3mm Product Construction





The information contained in this Data Sheet is intended to assist you in designing with Rogers'Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers Corporation or one of its subsidiaries.

© 2013 Rogers Corporation, All rights reserved. Printed in U.S.A., 1213-PDF, Publication #17-243