

## Gaskets materials

### Flexseal® FFKM FS 30239

---

**Description:** Flexseal® FFKM FS 30239 has excellent chemical corrosion resistance and is resistant to organic acids, inorganic acids, alkalis, esters, ethers, ketones, aldehydes, etc. Flexseal® FFKM FS 30239 has excellent heat resistance and hot air ageing properties. It is suitable for environments with high temperatures, such as semiconductor processes. Flexseal® FFKM FS 30239 has a maximum working temperature of 230°C.

---

**Applications:** Flexseal® FFKM FS 30239 is mainly used for the production of sealing parts such as O-rings, washers, flanges, valve housings, flaps, pump housings and stators, metal bonded parts, diaphragms and profiles. Flexseal® FFKM FS 30239 is also used in the petrochemical industry, the aerospace industry and the semiconductor industry.

---

**Colour:** Black

---

**Forms of delivery:** Flexseal® FFKM FS 30239 can be supplied as a cut-to-size or stamped part. Other delivery forms on customer request.

---

## Flexseal® FFKM FS 30239

Properties	Test Method	Unit	Value
Hardness	ASTM D2240	Shore A	74
Modulus at 100%	ASTM D412 , 500mm/min	MPa	14,1
Tensile strength	ASTM D412 , 500mm/min	MPa	21,8
Elongation at break	ASTM D412 , 500mm/min	%	158
Compression set Compressibility at 25% 24h×200°C	ASTM D395B , 214 O-RING	%	13
Brittleness at low temperatures	ASTM D746-2007	°C	-20
High temperature resistance		°C	+230
Steam and hot amine resistance			No

### Chemical resistance

Acid	Excellent
Alkali	Very good
Alcohol	Excellent
Aldehyde	Excellent
Ammonia (room temperature)	Very good
Amine (>70°C)	Good
Ether	Excellent
Ester	Excellent
Ketone	Excellent
Superheated water,vapour	Excellent
Strong oxidant	Good
Oxirane,epoxypropane	Very good
Aromatic alkyl,aliphatic hydrocarbon based oil	Excellent

## Flexseal® FFKM FS 30239

**Trademark information:** Flexseal® is a registered trademark of company Dr. Dietrich Müller GmbH, Germany.

---

**Please note:**

The information in this data sheet is based on our current knowledge and experience. They do not disengage the fabricator and user from own tests and inspections because of the plenty of possible effects. There is no judicial binding assurance of certain properties or of the qualification for a concrete application in our declaration. We recommend consulting us in individual cases. The acceptor of our products has to observe possible industrial property rights as well as present laws by himself

---