

## Thermally conductive products

### Thermiglue® TL 23026

---

#### Description:

Thermiglue® TL 23026 is a one-component thermally conductive gel with low deformation force and high thermal conductivity. Thermiglue® TL 23026 has a non-flowing, plastic consistency with low thermal resistance and excellent insulating properties. Due to its ability to automatically fill micro-gaps, Thermiglue® TL 23026 ensures an optimal contact surface between electronic components and cooling modules. In contrast to thermally conductive pastes, Thermiglue® TL 23026 shows no sedimentation or tendency to flow. Thermiglue® TL 23026 is suitable for screen printing, squeegee and dispensing applications with standard equipment and thus enables efficient and clean processing.

---

#### Properties:

Thermiglue® TL 23026 has high thermal conductivity, low thermal resistance, good wettability and insulating properties, no flowing or settling, reliably fills uneven surfaces, is soft and stress-free, compressible up to 0.1 mm, is compatible for automatic dosing technology and has an adjustable layer thickness.

---

#### Applications:

Thermiglue® TL 23026 is used in wireless electronic devices, communication and network technology, automotive electronics and control units, cooling modules and housings of power electronics, servers, processors, memory and graphics chips.

---

#### Colour:

gray

---

## Thermiglue® TL 23026

**Forms of delivery:** Thermiglue® TL 23026 is supplied in the sizes 30ml, 55ml and 300ml. Other containers on customer request.

**Storage conditions:** Thermiglue® TL 23026 should be stored at room temperature in dry rooms.

| Properties                  | Test Method    | Unit                 | Value              |
|-----------------------------|----------------|----------------------|--------------------|
| Color                       | Visual         | -                    | gray               |
| Specific gravity            | ASTM D792      | g/cm <sup>3</sup>    | 3,5                |
| Extrusion Rate              | 90psi@φ2.45 mm | g/min                | ≥10                |
| Thickness after compression | -              | mm                   | 0,2                |
| Weight loss                 | @150°C240H     | %                    | ≤0,2               |
| Breakdown Voltage           | ASTM D149      | KV/mm                | ≥5                 |
| Volume resistivity          | ASTM D257      | Ω·cm                 | 1×10 <sup>11</sup> |
| Continuous Use Temp         | -              | °C                   | -40 to +150        |
| Thermal conductivity        | ISO 22007-2    | W/mK                 | 7,0                |
| Thermal impedance           | ASTM D5470     | °Cin <sup>2</sup> /W | 0,023              |

**Trademark information:** Thermiglue® is a registered trademark of Dr Dietrich Müller GmbH, Germany.

**Please note:**

The information in this technical data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during application, it does not exempt the processor and user from carrying out their own tests and trials. A legally binding guarantee of certain properties or suitability for a specific application cannot be derived from our information. Depending on the individual case, we recommend consulting us. The recipient of our products is responsible for observing any industrial property rights and existing laws.