

## Electrical insulating material

### Flexiso® 3030 FI 11030

---

**Structure:** Flexiso® 3030 FI 11030 is made from pure binder-free and unbleached sulphate pulp.

---

**Characteristics:** Flexiso® 3030 FI 11030 is calendered and has good tensile and compressive strength as well as good compatibility and impregnation with impregnating and trickle resins. Flexiso® 3030 FI 11030 is used in applications of insulation class A (105°C).

---

**Application:** Flexiso® 3030 FI 11030 is used in electrical applications as end insulation in stators and rotors and for bobbins in transformers.

---

**Form of Supply:** Flexiso® 3030 FI 11030 is supplied as standard in thicknesses of 0.7 to 4.0 mm, according to the thickness the format is 640 x 800 or 800 x 1000 mm. Additional formats, blanks, die-cut and formed parts are manufactured to customer requirements and on special request.

---

**Storage conditions:** Flexiso® 3030 FI 11030 can be stored indefinitely under normal conditions (20 ° C, 50% RH) and in the original packaging. The material should be protected against humidity, dryness, direct sunlight and UV radiation as well as any heat effects.

---

## Flexiso® 3030 FI 11030

Property	Test method	Unit	Value								
			0.70 ± 0.05	0.80 ± 0.05	0.90 ± 0.05	1.00 ± 0.07	1.50 ± 0.10	2.00 ± 0.10	2.50 ± 0.10	3.00 ± 0.15	4.00 ± 0.20
Thickness	IEC 641	mm	0.70 ± 0.05	0.80 ± 0.05	0.90 ± 0.05	1.00 ± 0.07	1.50 ± 0.10	2.00 ± 0.10	2.50 ± 0.10	3.00 ± 0.15	4.00 ± 0.20
Area weight	IEC 641	kg/m <sup>2</sup>	0.91 ± 10%	1.04 ± 10%	1.17 ± 10%	1.30 ± 10%	1.95 ± 10%	2.60 ± 10%	3.25 ± 10%	3.90 ± 10%	5.00 ± 10%
Area yield	IEC 641	m <sup>2</sup> /kg	1.1	1.0	0.9	0.8	0.5	0.4	0.3	0.3	0.2
Density	IEC 641	g/m <sup>2</sup>	1.25 - 1.35	1.25 -1.35	1.25 -1.35	1.25 - 1.35	1.25 -1.35	1.25 -1.35	1.25 -1.35	1.25 -1.35	1.25 - 1.35
Humidity content	IEC 641	%	≤8	≤8	≤8	≤8	≤8	≤8	≤8	≤8	≤8
Ash content	IEC 641	%	≤3	≤3	≤3	≤3	≤3	≤3	≤3	≤3	≤5
Tensile strength											
longitudinal	IEC 641	N/mm <sub>2</sub>	≥85	≥85	≥85	≥85	≥90	≥90	≥90	≥90	≥90
crosswise	IEC 641	N/mm <sub>2</sub>	≥40	≥40	≥40	≥40	≥43	≥43	≥43	≥43	≥43
Elongation											
longitudinal	IEC 641	%	≥7.0	≥7.0	≥7.0	≥7.0	≥7.0	≥7.0	≥7.0	≥7.0	≥7.0
crosswise	IEC 641	%	≥12.0	≥12.0	≥12.0	≥12.0	≥12.0	≥12.0	≥12.0	≥12.0	≥12.0
Shrinkage	IEC 641	%	≤2.0	≤2.0	≤2.0	≤2.0	≤2.0	≤2.0	≤2.0	≤2.0	≤2.0
Conductivity of aqueous extract	IEC 641	μS/cm	≤200	≤200	≤200	≤200	≤200	≤200	≤200	≤200	≤200
Dielectric strength	IEC 641	kV/mm	≥13.0	≥13.0	≥13.0	≥13.0	≥12.0	≥12.0	k.A.	k.A.	k.A.

## Flexiso® 3030 FI 11030

---

**Trademark Information:** Flexiso® is a registered trademark of the company Dr. Dietrich Müller GmbH Germany.

---

**Information:**

The information in this Technical Data Sheet is based on our present knowledge and experiences. It does not release the user from conducting their own trials and examinations to determine the suitability of the product for his intended use. A legally obligatory warranty of certain characteristics or the suitability for a specific targeted application cannot be derived from our data. Depending upon individual cases we recommend consultation with us. Any patent rights as well as existing laws are to be considered by the receiver of our products as their own responsibility

---