

## Laminates

### Rigidiso® RI 40400

---

**Composition:** Rigidiso® RI 40400 is a manufactured polyester resin and glass cloth laminate and meets the following standards:

|               |            |
|---------------|------------|
| IEC 60893     | UP GM 203  |
| DIN 7735      | HM 2471    |
| BS (GB)       | 3953-UP 3  |
| NEMA L1 (USA) | GPO-3      |
| NF C26 (F)    | 153-Vm P2e |
| VSM (CH)      | S-UP GM 3  |
| MIL SPEC      | 24768/6    |

---

**Properties:** Rigidiso® RI 40400 is insulating up to insulation class F (155°C), furthermore it has very good mechanical properties. In addition to that it is environmentally neutral, free of asbestos, dioxin, cadmium and halogen. Rigidiso® RI 40400 is designed in accordance with flammability class UL 94 level V-0. Flammability classification complies with the EN 45545-2 standard.

---

**Applications:** Rigidiso® RI 40400 is used whenever good mechanical and electrical properties are required. Like for example at electrical constructions, distribution boxes, rail supports, etc.

---

**Delivery forms:** Rigidiso® RI 40400 is available in thicknesses of 0.15 mm – 150 mm as well as sheet (2440 x 1220 mm and 1150 x 2200 mm with a max. sheet size of 2440 x 1240 mm). Furthermore Rigidiso® RI 40400 can also be delivered as cut, milled, die-cut or water-jet cut parts. In addition it can be equipped with a special varnish to meet an CTI of more than 600.

---

Dr. Dietrich Müller GmbH



Dr. Dietrich Müller GmbH  
Zeppelinring 18  
D-26197 Ahlhorn

Tel.: +49 (0) 44 35 - 97 10 10  
Fax: +49 (0) 44 35 - 97 10 11  
Info@mueller-ahlhorn.com

Dr. Dietrich Müller GmbH

Zeppelinring 18 | D-26197 Ahlhorn | Tel.: +49 (0) 4435 97 10 10 | Fax: +49 (0) 4435 97 10 11  
info@mueller-ahlhorn.com | www.mueller-ahlhorn.com | Sitz der Gesellschaft: Ahlhorn  
Geschäftsführer: Dr. Michael Müller | AG Oldenburg: HRB 209026 | Ust. ID-Nr.: DE 295969093  
St.-Nr.: 68/207/07677 | Zertifiziert nach DIN EN ISO 9001:2015 | UL anerkannter Repacker E341377

- Elektroisierstoffe
- Dichtungen
- Wärmeleitprodukte
- Technische Folien

## Rigidiso® RI 40400

**Standard colour:** Rigidiso® RI 40400 is delivered in white colour.

**Storage conditions:** Rigidiso® RI 40400 can be stored unlimited under normal conditions (20°C, 50% rel. air humidity).

| Property                                                                                      | Test method | Unit              | Value                           |
|-----------------------------------------------------------------------------------------------|-------------|-------------------|---------------------------------|
| Density                                                                                       | ISO 1183    | g/cm <sup>3</sup> | ca. 1.9                         |
| Tensile strength                                                                              | ISO 527     | N/mm <sup>2</sup> | 124                             |
| Flame behaviour                                                                               | UL 94       | -                 | V-0/5 mm<br>S4/ST2/SR2<br>M2/F1 |
| Thermal class                                                                                 | IEC 60085   | -                 | F                               |
| Comparative tracking index                                                                    | IEC 60112   | CTI               | 600                             |
| Flexural strength untreated at 23°C                                                           | DIN 53452   | MPa               | 200                             |
| Impact resistance a <sub>n10</sub> und a <sub>n15</sub>                                       | DIN 53453   | kJ/m <sup>2</sup> | 187                             |
| Notch impact resistance a <sub>k10</sub>                                                      | DIN 53453   | kJ/m <sup>2</sup> | 150                             |
| Pressure resistance                                                                           | DIN 53454   | MPa               | 188                             |
| Splitting strength                                                                            | DIN 53463   | N                 | 2290                            |
| Resistance between plugs after 24 hours water storage at 23°C                                 | DIN 53457   | MPa               | 10570                           |
| 1 Minute test voltage in layer direction at 90°C after pre-treatment                          | DIN 53482   | Ohm               | 7.1 x 10 <sup>8</sup>           |
| 1 Minute test voltage vertical to layer at 90°C after pre-treatment                           | DIN 53481   | kV                | 40                              |
| Dielectric dissipation factor tan d – 50 Hz<br>96 hours 105°C<br>1 MHz 24 hours water storage | DIN 53481   | kV                | 34                              |

Dr. Dietrich Müller GmbH

## Rigidiso® RI 40400

| Property                        | Test method | Unit                | Value            |
|---------------------------------|-------------|---------------------|------------------|
| Dielectric constant             | DIN 53483   | max.                | 0.0092<br>0.0372 |
| Electrolytic corrosion          | DIN 53483   | »                   | 5                |
| Splitting strength              | DIN 53489   | max.                | A/B 1.4          |
| Light arc resistance            | DIN 53484   | Level               | 180 sec.         |
| Thermal conductivity            | DIN 52612   | W/m*k               | 0.3              |
| Coefficient of linear expansion | VDE 0304/2  | 10 <sup>-6</sup> /K | 17               |
| Limiting temperature            | VDE 0304/2  | °C                  | 155              |
| Incandescence resistance        | DIN 53459   | Level               | 2a               |
| Water absorption – 4 mm thick   | DIN 53459   | mg                  | 60               |

| Thickness    | 0.3 | 0.5 | 0.8 | 1.0 | 1.5 | 2.0 | 2.5 | 3.0 | 3.5 | 4.0 |
|--------------|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|
| Availability | ○   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   |

| Thickness    | 4.5 | 5.0 | 6.0 | 7.0 | 8.0 | 9.0 | 10.0 | 11.0 | 12.0 | 13.0 |
|--------------|-----|-----|-----|-----|-----|-----|------|------|------|------|
| Availability | ●   | ●   | ●   | ●   | ●   | ●   | ●    | ●    | ●    | ●    |

| Thickness    | 14.0 | 15.0 | 16.0 | 17.0 | 18.0 | 19.0 | 20.0 | 21.0 | 22.0 | 25.0 |
|--------------|------|------|------|------|------|------|------|------|------|------|
| Availability | ●    | ●    | ●    | ●    | ●    | ●    | ●    | ●    | ●    | ●    |

| Thickness    | 30.0 | 35.0 | 40.0 | 45.0 | 50.0 | 60.0 | 70.0 | 80.0 | 90.0 | 100.0 |
|--------------|------|------|------|------|------|------|------|------|------|-------|
| Availability | ●    | ●    | ●    | ○    | ○    | ○    | ○    | ○    | ○    | ○     |

● Pre-material on stock

○ Delivery time pre-material 2 weeks

**Trademark Information:** Rigidiso® is a registered trademark of the company Dr. Dietrich Müller GmbH, Germany.

Dr. Dietrich Müller GmbH

## Rigidiso® RI 40400

---

### Please note:

The information in this data sheet is based on our current knowledge and experience. They do not disengage the fabricator and user from own tests and inspections because of the plenty of possible effects. There is no judicial binding assurance of certain properties or of the qualification for a concrete application in our declaration. We recommend consulting us in individual cases. The acceptor of our products has to observe possible industrial property rights as well as present laws by himself

---

Dr. Dietrich Müller GmbH